

**Key Details:**

- Eastern Juniper, scientific name *Juniperus virginiana*
- Sizes stocked:
  - 5/4 x 6
  - 5/4 x 4
- Custom sizes available

**Specifications:**

Wood Common name .....	Eastern Juniper
Wood Scientific name .....	<i>Juniperus virginiana</i>
Color .....	Initial color is red/light brown
Grain .....	Knotty grain
Density @ 12% moisture .....	3.0 pounds per board foot
Durability .....	Highest rating from USDA
Hardness (Janka) .....	900
Resistance to decay and insect attack .....	Resistant to attack by decay fungi and termites.
Modulus of rupture .....	8,800 lbf/in <sup>2</sup>
Modulus of elasticity .....	880,000 lbf/in <sup>2</sup>
Maximum crushing strength .....	6,020 lbf/in <sup>2</sup>
Wood movement properties .....	Radial: 3.1%, Tangential: 4.7%, Volumetric: 7.8%, T/R Ratio: 1.5