

Key Details:

- Eastern Juniper, scientific name *Juniperus virginiana*
- Sizes stocked:
 - 1 x 6 (Actual ¾" thick with a 5" face)
 - 1 x 5 (Actual ¾" thick with a 4" face)
 - 1 x 4 (Actual ¾" thick with a 3" face)
- Milling profile is V-Groove or V4E:



Specifications:

Wood Common name	Eastern Juniper
Wood Scientific name	<i>Juniperus virginiana</i>
Color	Initial color is red/light brown
Grain	Knotty grain
Density @ 12% moisture	3.0 pounds per board foot
Durability	Highest rating from USDA
Hardness (Janka)	900
Resistance to decay and insect attack	Resistant to attack by decay fungi and termites.
Modulus of rupture	8,800 lbf/in ²
Modulus of elasticity	880,000 lbf/in ²
Maximum crushing strength	6,020 lbf/in ²
Wood movement properties	Radial: 3.1%, Tangential: 4.7%, Volumetric: 7.8%, T/R Ratio: 1.5