


Key Details:

- Sassafras, scientific name *Sassafras albidum*
- Sizes stocked:
 - 1 x 6 (Actual $\frac{3}{4}$ " thick with a 5" face)
 - 1 x 5 (Actual $\frac{3}{4}$ " thick with a 4" face)
 - 1 x 4 (Actual $\frac{3}{4}$ " thick with a 3" face)
- Milling profile is V-Groove or V4E:

**Specifications:**

Wood Common name	Sassafras
Wood Scientific name	<i>Sassafras albidum</i>
Color	Initial color is light brown
Grain	Tight grain
Density @ 12% moisture	2.75 pounds per board foot
Durability	Highest rating from USDA
Hardness (Janka)	630
Resistance to decay and insect attack	Resistant to attack by decay fungi and termites.
Modulus of rupture	9,000 lbf/in ²
Modulus of elasticity	1,120,000 lbf/in ²
Maximum crushing strength	6,600 lbf/in ²
Wood movement properties	Radial: 4.0%, Tangential: 6.2%, Volumetric: 10.3%, T/R Ratio: 1.6